

## deflexx 100

deflexx 100 is a very elastic high performance - foil adhesive tape for durable airtight bonding of wall panels with floor and ceiling.

Product guarantee: 10 years

Recommended system product: doitBau **devapp, devaioo, deplann, Dichtmasse DK, detakk, defixx**

### Technical Facts as stated by DIN 4102-8

|                           |  |
|---------------------------|--|
| Adhesive                  | Acrylate dispersion (solvent-free)             |
| Adhesion carrier          | LDPE- foil                                     |
| Carrier color             | Black  |
| Adhesion intercarrier     | Polyester armoring                             |
| Cover material            | silicone paper brown                           |
| Thickness (without cover) | approx. 0,25 mm                                |
| Adherency                 | 14 N/ 1 cm DIN EN 1939                         |
| Temperature               | -40 / +100 °C                                  |
| Aging resistance          | Very good                                      |
| Moisture resistance       | good   |
| Working temperature       | > -10°C (Substrate has to be dry and ice free) |

### Get-up

|                       |                    |
|-----------------------|--------------------|
| Length of roll        | 25 m               |
| Width of roll         | 100 mm             |
| m <sup>2</sup> / roll | 2,5 m <sup>2</sup> |
| kg / roll             | approx. 1,25 kg    |
| Reference number      | 600102             |

### Guarantee

doitBau grants 10 years on all characteristics which are warranted in the manual. However, this guarantee is excluded,

- in case of a processing or usage which deviates from what is stated in the manual.
- in case of abnormal chemical and/or mechanical influences on the product.
- in case of multilayered lengths, if the lengths haven't got sufficient inner cohesiveness (insufficient load carrying capacity by separation of layers).
- for sauna and swimming pool construction.

Prior to using the product tackifying tests have to be conducted on site in any case. It is possible that this manual is inoperative due to recent changes in knowledge and development. The most valid manual can be found at [www.doitBau.com](http://www.doitBau.com)